

**Falex Test Results<sup>1</sup>**  
(Run to Failure)

<b><u>Product</u></b>	<b><u>Load Capability (LBS)</u></b>
RF 150 with 1.25% S8478*	1300
RF 300	560
RF 300 with 1.25% S8478*	1350
2.00% S8478*	1310
1.25% S8478* (R-12 Bubble)	1330
2.0% S8478*	1330
0.1% Lubrizol 1097	880
0.5% S8478*	1075
Mobil DTE	1240

**\*Synoad 8478**

**<sup>1</sup>All with R-22 bubbled through unless otherwise indicated**

