

## Acetylene Black -01

### Description

High purity Acetylene Black grades in powder form with structural and electrical properties that make it ideal for a variety of applications such as batteries, conductive coatings, and rubber compounds.

### Properties

SPECIFICATION PROPERTIES	AB 50%-01	AB 75%-01	AB 100%-01	ABHC-01 (high conductivity)
Ash Content, wt%	<0.05	<0.1	<0.5	<0.1
Grit (325 sieve), wt%	<0.03	<0.01	<0.05	<0.03
Moisture, wt%	<0.08	<0.2	<0.2	<0.2
Electrical Resistivity, ohm-cm	≤0.25	≤0.25	≤0.25	≤0.25
pH Value	6 - 8	6 - 8	6 - 8	6 - 8
Acetone Absorption ml/5g	33 - 36	27.5 - 30.5	>14	29.5 - 32.5*
Oil Absorption Number (OAN), ml/100g	270 - 325	250 - 300	187 - 202	330 - 400
TYPICAL PROPERTIES				
Hydrochloric Acid Absorption Number, ml/g	4.4	4.5	3	7
Carbon Content, %	99.9	99.9	99.9	99.9
Iodine Absorption Number mg/g	81	97	91	130
Bulk Density, g/ml	0.090 - 0.120	0.14 - 0.18	0.17 - 0.23	0.05 - 0.09
BET Surface Area, m <sup>2</sup> /g	60 - 80	60 - 80	60 - 80	100 - 120
Mean Particle Size, nm	25 - 45	25 - 45	25 - 45	25 - 45

\*ml/3g

### Packaging

Available in paperbags, polybags, and super sacks.

No warranties, express or implied, including warranties of merchantability or fitness for a particular use are made with respect to the products described herein. Nothing contained herein shall constitute permission or a recommendation or inducement to practice any invention covered by a patent without the permission of the patent owner. Customers/users are advised to test the product in advance to make certain it is suitable for their particular production conditions and use or uses of the product. Seller shall not be liable for and the customer assumes all risk and liability for any use or handling of the product.