

RF 150
Shell Four-Ball Wear Test
(ASTM D-2266)¹

<u>Oil</u>	<u>Scar Diameter, mm</u>
RF 150	0.50
RF 150, 0.5% S8478*	0.22
RF 300	0.45
RF 300, 0.5% S9478*	0.25
Mineral Oil	0.50

¹ 1800 RPM, 5 Kg, 75 °C (158 °F), 1 Hour

*** Synoad 8478**

