

Elastomer Compatibility

Linear Swelling, % *150 °F, 14 Days*

<u>Elastomer</u>	<u>RF 150</u>	<u>Mineral Oil</u>
Neoprene W	10.1	12.6
Buna N	0.60	1.00
Hypalon 40	4.80	7.60
Butyl Rubber	21.2	27.0

Weight Gain, % *150 °F, 4 Months*

<u>Material</u>	<u>RF 150</u>	<u>Mineral Oil</u>
Neoprene	10	13
Nylon 66	-1	-1
Mylar	0	0
Buna N	0	2
Viton A	0	0
Polypropylene	10	12

