

Electrical Grade Polybutenes

Description

Soltex synthetic dielectric fluids are alkylate/polybutene based insulating cable oils compatible with materials of construction that provide optimum high oxidative/thermal stability during manufacture and protection in service.

Properties

SPECIFICATION PROPERTIES	ASTM	PB 6E	PB 8E	PB 011E	PB 015E	PB18E	PB 24E	PB 1500E	PB 32E
Kinematic Viscosity (cSt)									
Min	D-445	21	94	18	32	70	190	322	579
Max		45	130	23	37	95	240	365	729
Temp, °C		40	40	98.9	98.9	98.9	98.9	98.9	98.9
Flash Point (COC), °C									
Min	D-92	110	120	120	120	120	180	180	200
Color,									
Max	D-1500	1	1	1	1	1	1	1	1
Water, ppm									
Max	D-1533	35	35	35	35	35	35	35	35
Acid Number, mg KOH/g									
Max	D-974	0.02	0.02	0.02	0.02	0.02	0.02	0.02	0.02
Dielectric Strength, 23 °C, KV									
Min	D-877	35	35	35	35	35	35	35	35
Dielectric Dissipation Factor, 100°C Initial/60 Hz, Max	D-924	0.001	0.001	0.0005	0.0005	0.0005	0.0005	0.0005	0.0005
TYPICAL PROPERTIES									
Saybolt Viscosity (SUS) , Temp 98.9 °C	D-2161	32-45	55-66	90-110	155-175	325-445	880-1100	1500-1700	2700-3400
Specific Gravity, 15.6°/15.6°C	D-1298	0.83-0.85	0.84-0.86	0.85-0.88	0.85-0.88	0.86-0.90	0.88-0.90	0.88-0.91	0.89-0.91
Density, lb / gal	D-1298	6.91	7.16	7.24	7.17	7.32	7.41	7.48	7.5
Pour Point , °C									
Max	ASH-86	-40	-35	-20	-20	-15	2	5	8
Dielectric Dissipation Factor, After 96 h/115°C/60 Hz	D-1935	0.002	0.002	0.002	0.001	0.001	0.001	0.001	0.001

No warranties, express or implied, including warranties of merchantability or fitness for a particular use are made with respect to the products described herein. Nothing contained herein shall constitute permission or a recommendation or inducement to practice any invention covered by a patent without the permission of the patent owner. Customers/users are advised to test the product in advance to make certain it is suitable for their particular production conditions and use or uses of the product. Seller shall not be liable for and the customer assumes all risk and liability for any use or handling of the product.