## **OPTICOOL-MIL FLUID**

- Cools more efficiently than other fluids
- Superior heat transfer capabilities
- Higher oxidation and inhibitor stability
- Exceptional for extreme temperature applications
- Compatible with Mineral Oil
- Complies with US Military
  Spec MIL-C-87252A





1320 E. Commerce St. Tyler, TX 75702 800-796-0220 sales@dsiventures.com

**DSIVentures.com** 

## Synthetic Heat Transfer and Insulating Fluid for Military and Aerospace Equipment

OptiCool-MIL Fluid is a highly efficient dielectric heat transfer fluid used to cool electrical equipment in military and aerospace applications. OptiCool-MIL has excellent heat transfer characteristics and a very high dielectric strength.

Containing advanced oxidation inhibitors, it provides longer service life at high temperatures. Compared to standard transformer oil, OptiCool-MIL biodegrades faster and has better heat transfer characteristics. Gallon for gallon, OptiCool-MIL Fluid is almost 10% lighter than mineral oil.

OptiCool-MIL's enhanced electronic



cooling performance allows equipment to be smaller in size and minimize the operating temperatures in any equipment.

## Used to Lower Temperatures in Applications:

- Chemical process cooling
- Immersion of electronic circuit boards
- Cooling of radar and transmission equipment
- Exceptional low temperature fluidity

TYPICAL CHARACTERISTICS - Compared with ASTM D3487, Guide for Mineral Insulating Oils		
Characteristic & ASTM method	OptiCool –MIL Fluid	Transformer Oil
Flash Point, D92 °C	160	145 min
Viscosity, D88, cSt. @ 40 °C	5.0	12.0 max
Viscosity, D88, cSt. @ 100 °C	1.7	3.0 max
Specific Gravity, D1298, 20 °C	0.798	0.91 min
Pour Point, D97, °C	-66	-40 max
Appearance	Clear	Clear
Dielectric Breakdown,D1816, kV	58	35 min
Dissipation Factor, D924, 100 $^{\circ}\text{C},$ %	0.01	0.30 max

Copyright © DSI Ventures, Inc. All rights reserved. DSI makes no representations regarding the suitability of any product for a given application. Warranties are limited to product characteristics only.